



ORGI CHEMIE FZ LLC

OCPOL 701

Ocpol 701 is a clear Pre-Accelerated orthophthalic unsaturated polyester resin. It is highly water resistance. Due to its outstanding stability and excellent performance it is use in boats water tanks, bath tubs shower tub etc.

Recommendation for Laminating:

Parts by weight:

Ocpol 701	100
Catalyst K 10	2ml

Applications:

- To start the curing reaction, take 100 parts of resin.
- Catalyst K 10 should be added to the resin system shortly before application to initiate the polymerization reaction.
- It is important to add the catalyst in carefully measured amounts to control the polymerization. Too much catalyst will cause too rapid a gelation time, whereas too little catalyst will result in under cure.
- Care must be taken to avoid explosive violence. Do not mix catalyst and cobalt octate or any accelerator together.

Properties of Liquid Resins:

Appearance.	Clear
Viscosity at 25°C (Brookfield , sp. 3@60 rpm	300 - 400 cps.
Gel Time at 25°C	10 – 15 min
25°C - 35°C (a)	14 – 24
25°C – Peak (b)	<40
b/a	Less than 2
Acid value mg KOH/g	< 26
Solid content %	58±2
Specific Gravity at 25°C	1.10 – 1.11
Peak Temperature	>170

Properties of fully cured resins (unfilled casting):

Barcol hardness (Model GYZJ 934 – 1)	43 - 47
Water absorption 24 h at 23°C	15 - 18 mg
Elongation at break at 20°C	1.9 – 2.2 %
Tensile Strength	70 - 75 Mpa
Tensile Modulus	3500 - 3750 Mpa
Flexural Strength	120 - 130 Mpa
Flexural Modulus	3600 - 3800 Mpa
Heat Deflection Temperature	70 - 75°C

Packing:

Ocpol 701 is supplied in 220 Kg new steel drums with close top.

Safety:

Due attention should be given to the precautions for handling chemicals provided in our Material Safety Data Sheet.

Remarks:

The information submitted in this publication is given in good faith but without warranty, In view of the many factors that may affect the application, users are recommended to carry out their own trials to determine the suitability of the product for their practical requirements. We cannot accept responsibility for any damage or loss resulting from the use of this information.

ORGI CHEMIE FZ LLC

P.O.BOX :6287,Ras Al Khaimah, U.A.E. [Tel:+971 7 2432925](tel:+97172432925),[Fax:+971 7 2432926](tel:+97172432926)

Email:admin@orgichemie.com Website:www.orgichemie.com